

CEDRIA White Australia wood stain Technical Sheet

Outdoor Range

Product Description

Water-based, brilliant white wood stain. Highly water-repellent. Blocks secretions and tannins and prevents the stains they cause. The brilliant white is long-lasting even on dark, resinous, tannic or copper-treated surfaces.

Properties

- Offers great resistance to weathering.
- Breathable.
- Rapid drying.
- It contains broad spectrum biocides to protect the film against fungal attacks and provide an effective film protection
- Environmentally friendly.

Recommended Uses

Especially for resinous softwoods and tannic tropical woods: doors, pergolas, decking and other wooden items. Exterior – Interior.

Technical Characteristics

Resin	Fine particle acrylic
Finish	Satin
Odour	Odourless
Viscosity	Brookfield 600 – 1000 mPa.s (L2, 20 25°C)
Density (20°C)	1.14 kg/l
Solvent Type	Water
VOC	It contains 20 g / l. Limit value 2004/42/CE-IIA cat. i) is VOC max. 140. g / l (2010)
Drying	Touch dry: 1-2 hours. Repainted: 2 hours
Application Conditions	Maximum Relative Humidity 65%. Temperature between 5° and 35°
Storage	Conserve inside at temperatures between 5°C and 35°C
Container sizes	750ml, 4l and 20l
Utensils and Cleaning	Brush, roller or spray-gun. Clean with water
Colours	Brilliant White
Coverage	10-12m ² /l depending on state of surface and wood type

Safety

- All current legislation must be followed in the case of storage and handling.
- Storage Life: 2 years in sealed containers and at storage conditions as recommended in the Technical Characteristics section.
- Prevent the product or product residues coming into contact with water courses. Remember: the care and protection of the environment is the legacy for our future generations.
- Keep out of the reach of children.

Quality Guarantee

CEDRIA products have been developed, manufactured and sold under the most rigorous quality standards. These recommendations are made in accordance with the current state of our knowledge and provide general information about the application and use of the products. Given the variety of substrates, uses and application techniques, the purchaser/user remains responsible for checking the materials, their application and the final result. For this reason, the purchaser/user is advised to test the product prior to the final application.

Application and Preparation of the wood

It is essential to prepare the wood properly before applying the wood stain:

1. The wood should be dry (with less than 18-20% humidity).
2. The wood should be free from dust, grease, residues and other substances.
3. Before applying the wood stain, it is recommended to sand the wood in the direction of the grain to open up the pores and improve adhesion. VERTICAL WOOD: P80 Sandpaper. HORIZONTAL WOOD: P40 Sandpaper. Avoid sanding between coats.
4. Product is ready to use (Only when using a spray-gun, if necessary, dilute with 5% water, preferably distilled).
5. Stir (do not shake) the product vigorously with a spatula before using.

New Wood

Softwoods – Pine, Spruce.

- It is essential to prepare the wood before applying the wood stain. See the section on Application and Preparation of wood.
- In addition, for insecticidal treatment apply 1 coat of CEDRIA FONDO*¹ before applying the wood stain. (In the case of spruce, due to its low impregnability, it is recommended where necessary to apply a coat of CEDRIA FONDO between the first and second coat of CEDRIA LASUR BLANCO AUSTRALIA).
- Apply 2 coats of CEDRIA LASUR BLANCO AUSTRALIA. Usage 100 g/m² per coat. Drying time between coats 2 hours.

Hardwoods - Chestnut and Oak rich in tannins.

- It is essential to prepare the wood before applying the wood stain. See the section on Application and Preparation of wood.
- Apply 1 coat of CEDRIA FONDO BLOQUEA TANINOS*¹ to prevent black stains caused by the tannins.
- Apply 2 coats of CEDRIA LASUR BLANCO AUSTRALIA. Usage 100 g/m² per coat. Drying time between coats 2 hours.

Deep-treated woods.

CEDRIA LASUR BLANCO AUSTRALIA is compatible with woods treated with hydrosoluble salts and other organic solvent treatments if and when the drying times have been observed before application.

- It is essential to prepare the wood before applying the wood stain. See the section on application and preparation of wood.
- Apply 2 coats of CEDRIA LASUR BLANCO AUSTRALIA. Usage 100 g/m² per coat. Drying time between coats 2 hours.

Wood that is worn or in a poor state

- It is essential to prepare the wood before applying the wood stain. See the section on application and preparation of wood.
- Remove traces of previous products before sanding the wood in the direction of the grain (see the section on preparation of the wood) or stripping the wood with CEDRIA DECAPANTE*¹.
- Apply 2 coats of CEDRIA LASUR BLANCO AUSTRALIA. Usage 100 g/m² per coat. Drying time between coats 2 hours.

Maintenance

To be followed when the colour loses brightness or has faded due to weathering and erosion.

- Simply clean the surface with water using a high-pressure jet (Pressure washer. Guide pressure 80-120 bar) and allow to dry for between 12 and 24 hours or lightly sand in the direction of the grain (see section on preparation of the wood).
- Apply 2 coats of CEDRIA LASUR BLANCO AUSTRALIA. Usage 100 g/m² per coat. Drying time between coats 2 hours.

Additional Recommendations

- To improve the finish and strengthen the solar protection, after applying the last coat of CEDRIA LASUR BLANCO AUSTRALIA and observing the drying times, apply a coat of CEDRIA SOL LASUR INCOLORO*¹ (Thin finish coat) or of CEDRIA BARNI SOL INCOLORO*¹ (Thick finish coat).
- For woods such as Oregon or Longleaf Pine which are resinous or have resinous knots, after sanding and before applying the wood stain, it is recommended to wipe the wood thoroughly with a cloth impregnated with CEDRIA WOOD NET*¹.
- CEDRIA LASUR BLANCO AUSTRALIA is compatible with previous or subsequent applications of most water-based wood stains and varnishes. For greater security, it is recommended to test the product, as is the case with other types of repainting.
- Due to the nature of the resin used, CEDRIA LASUR BLANCO AUSTRALIA may present incompatibilities if the emulsion is mixed with another of different characteristics.
- It is very important to avoid applying the product in hours of maximum direct sunlight. When the wood is too hot, the polymerisation of the resins is impaired. As an emergency solution and to avoid the effects caused by rapid evaporation of the water, it is recommended to lightly wet the wood with a small amount of water. It is also recommended not to apply the products in temperatures less than 5°C.
- Drying times will vary according to temperature and relative humidity.
- The performance and behaviour of the product may vary depending on the type of wood.
- To ensure maximum protection outdoors avoid sanding between coats.
- When sanding avoid using metallic scouring pads, steel wool or any other tool that can leave metal remnants.

*1: See the Technical Sheet for this product.